

Exaton Ni72HP

Exaton Ni72HP is filler material for joining NiCrFe alloys, 9% Ni steels used at cryogenic temperatures, stainless steels to carbon steels, high service temperature NiCu alloys to carbon steels and NiCu alloys to nickel alloys. Exaton Ni72HP can be used in air up to 1175°C (2145°F) and in sulphur dioxide atmospheres up to 800°C (1470°F). Recommended flux is Exaton 50SW.

Specifications	
Classifications	SFA/AWS A5.14 : ERNiCr-3 EN ISO 18274 : S Ni 6082 (NiCr20Mn3Nb)
Approvals	VdTÜV : 03770

Approvals are based on factory location. Please contact ESAB for more information.

Typical Wire Composition %									
C	Mn	Si	S	P	Ni	Cr	Mo	Cu	N
<=0.03	3.0	0.1	<=0.010	<=0.010	72.5	20.0	<=0.2	<=0.05	<=0.05

Typical Wire Composition %			
Ti	Co	Fe	Nb+Ta
0.4	<=0.10	<=1.0	2.6