

Exaton 16.5.1 (GTAW)

16.5.1 is a filler material for joining EN 1.4418 and similar steels. It is also used for overlay welding. The weld metal has excellent resistance to cavitation and is used typically for shafts, propellers, pumps and valves in for example, hydropower generation.

Specifications

Classifications	EN ISO 14343-A : W 16 5 1
Approvals	CE : EN13479

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Austenitic/Martensitic/Ferritic - 16% Cr - 5% Ni - 1% Mo - Low C
Shielding Gas	I3 (EN ISO 14175)

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
PWHT 590 Deg C, 4 h			
PWHT 4 hour(s) 590 °C	470 MPa	850 MPa	22 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
PWHT 590 Deg C, 4 h		
PWHT	20 °C	80 J

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	V	Al
0.01	1.4	0.3	0.009	0.015	5.5	16.2	1.0	0.04	0.006

Typical Wire Composition %

Cu	N	Nb	Ti	Co
0.01	0.02	0.01	0.01	0.03