

## OK Autrod 19.12

A continuous solid copper wire for welding of oxygen free, pure copper and low alloyed copper. OK Autrod 19.12 is alloyed with tin, and has good flow properties. The weld is easily workable. For welding of large work pieces and heavy thickness preheating is recommended.

### Specifications

<b>Classifications</b>	SFA/AWS A5.7 : ERCu EN ISO 24373 : CuSn1
------------------------	---

<b>Alloy Type</b>	Copper (Cu + 0.7 % Sn)
-------------------	------------------------

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
As Welded	75 MPa	220 MPa	30 %

### Typical Wire Composition %

Mn	Si	Cu	Fe
0.2	0.2	Bal	0.05

### Recommended Welding Parameters

Current	Wire Diameter	Voltage	Wire Feed Speed
60-165 A	0.8 mm	13-17.5 V	4.0-13.0 mm/min
80-210 A	1.0 mm	12.5-18 V	4.0-12.0 mm/min
150-320 A	1.2 mm	16-29 V	5.0-11.5 mm/min