

OK AUTROD 16.53

A corrosion resistant, chromium-nickel alloyed solid wire for joining stainless steels to non-alloy or low-alloy steels and for welding austenitic stainless alloys of the 24Cr-13Ni types. The alloy is also used for welding buffer layers on C-Mn/low-alloy steels.

Specifications

Classifications	SFA/AWS A5.9 : ER309L
-----------------	-----------------------

Alloy Type	Austenitic Cr-Ni
Shielding Gas	M12, M13 (EN ISO 14175)

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
As Welded	420 MPa	600 MPa	35 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
As Welded	-60 °C	80 J

Typical Wire Composition %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu
0.02	1.70	0.40	0.010	0.025	12.30	23.50	0.10	0.10

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
0.8 mm	55-160 A	15-24 V	4.0-17.0 m/min	1.0-4.1 kg/h
1.2 mm	100-300 A	15-29 V	3.0-14.0 m/min	1.6-7.5 kg/h