

OK 74.79

OK 74.79 is a high recovery, LMA electrode suitable for welding high tensile steels for structures. Very suitable for enclosed joint welding of rail and for cladding on rail when a hardness of about 250 HV is desired. The moisture content of the coating is very low, which makes OK 74.79 suitable when preheating cannot be applied. The risk of grain boundary cracking is very low when welding with OK 74.79.

Welding Current	AC, DC+
Alloy Type	High-tensile
Coating Type	Zircon Basic

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
Stress Relieved	600 MPa	670 MPa	23 %
ISO			
As Welded	600 MPa	670 MPa	23 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
Stress Relieved	20 °C	80 J
Stress Relieved	-40 °C	37 J
Stress Relieved	-60 °C	25 J
Stress Relieved	-20 °C	47 J
ISO		
As Welded	-60 °C	30 J
As Welded	-40 °C	50 J
As Welded	-20 °C	60 J
As Welded	20 °C	105 J

Deposition Data

Diameter	Current	Voltage	kg weld metal/kg electrodes	Number of electrodes/kg weld metal	Fusion time per electrode at 90% I max	Deposition Rate
3.2 x 450 mm	100-160 A	23 V	0.66	24.0	75 sec	2.00 kg/h
4.5 x 450 mm	200-300 A	31 V	0.67	12.0	77 sec	3.90 kg/h
5.6 x 450 mm	290-420 A	40 V	0.67	8.0	72 sec	6.30 kg/h