

OK Autrod 13.28

A copper coated, Ni-alloyed (2,4% Ni), solid wire for GMAW of low-alloyed and low temperature steels in applications such as vessels, pipes and in the offshore industry with a minimum yield strength less than 470 Mpa. The wire provides a good impact toughness down to -60C.

Specifications

Classifications	EN ISO 14341-A : G 46 6 M21 2Ni2 EN ISO 14341-A : G 2Ni2 SFA/AWS A5.28 : ER80S-Ni2
Approvals	CE : EN 13479 DNV-GL : V YMS (M21) UKCA : EN 13479 VdTÜV : 06852

Approvals are based on factory location. Please contact ESAB for more information.

Alloy Type	Low alloyed (2.5 % Ni)
Shielding Gas	M21 (EN ISO 14175)

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
EN Ar/20CO2 (M21)			
As Welded	540 MPa	630 MPa	28 %
AWS Ar/1-5O2 (M13)			
Stress Relieved 1 hour(s) 620 °C	540 MPa	630 MPa	29 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
EN Ar/20CO2 (M21)		
As Welded	-60 °C	60 J
As Welded	-40 °C	100 J
As Welded	0 °C	130 J
AWS Ar/1-5O2 (M13)		
Stress Relieved	-62 °C	131 J
Stress Relieved	0 °C	162 J
Stress Relieved	-29 °C	168 J

Typical Wire Composition %

C	Mn	Si	Ni
0.08	1.04	0.53	2.36

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	V	Al
0.1	1	0.4	0.01	0.01	2.4	0.05	0.1	0.001	0.01

Typical Weld Metal Analysis %

Cu	Ti+Zr
0.15	0.05

Deposition Data

Diameter	Current	Voltage
0.8 mm	40-170 A	16-22 V

OK Autrod 13.28

Deposition Data

Diameter	Current	Voltage
1.0 mm	80-280 A	18-28 V
1.2 mm	120-350 A	20-33 V